

## Technical data sheet

# PU FOAM STANDARD HAND HELD B3

# 22

## Description

Polyurethane Foam is installation and insulation polyurethane foam expanded by foaming and hardening of the fluid reaction mixture by the effect of aerial moisture.

## **Application**

- mounting and sealing of wooden, plastic and metallic window and external door frames, metallic and wooden doorframe and other structural parts
- insulation of hot water plumbing, hot water boilers, refrigeration equipment, bath tubs, shower trays
- sealing of gaps, cracks and cavities which cannot be filled with other sealing materials, sealing of plumbing, heating and gas piping and electric wiring
- grouting timbered buildings

### Application procedure

- Remove dust, grease and other contamination from the surface. Before the foam application the surface may be wet, but free from frost or ice.
  - NOTICE: PU foam is non-stick to surfaces: PE, PP, PTFE and silicone.
- 2 The optimal can temperature for application is +15°C to +20°C. The maximum allowed temperature difference between the ambient and the can is 5°C. Do not exceed the maximum allowed temperature interval for application from +5°C to +35°C.
- 3 Moisten surfaces with water applied from a spray bottle. Shake the can vigorously at least for 1 minute. Screw the plastic applicator on the valve. Bottle working position is the valve facing downwards. The amount of ejected foam can be regulated by pulling the applicator handle. If the cavity is wider than 5 cm we recommend to fill it in layers with maximal width of 2 cm. Wet the surface of each fresh foam layer and continue by adding other layer(s) until the space is filled up. The foam will expand during curing; therefore, fill the space only up to 1/2. Volume and quality of cured foam is influenced by the relative air humidity. Intensive moistening is necessary if relative air humidity is below 35 %.
- 4 Cured foam you can cut by a knife. The surface of cured PU foam must be protected from a long-term UV radiation.
- Fresh foam can be removed by PU CLEANER, cured foam mechanically only. When the work is interrupted for more than 10 15 min, there is necessary to clean up application tube and by PU CLEANER.

#### Safety and protection of health

When using this product wear protective glasses and gloves. More information is contained in the MSDS.

### **Specifications**

F	orm	foaming liquid
С	olour	light cream, blue, green, grey
С	<mark>Odour</mark>	of hydrocarbons
	laximum application temperatures ange	+5°C to +35°C
	Optimum can temperature for oplication	+15°C to +20°C
	linimum contact surface emperature	0°C
T	ack free time (TM1014-2013) *	12minutes
С (Т	utting time (strip of 2 cm diameter) M1005-2013) *	max. 40 minutes
Fi	inal curing time *	12 hours
D (F	ensity of freely expanded foam N 03) *	18 – 22 kg/m³
D	ensity of foam in gap (PN05) *	22 – 25 kg/m³
	oam yield of 750 ml can M1007-2013) *	28 – 32 litres
	imensional stability M1004-2013) *	max. ±5%
	ire class (DIN 4102)	B3

Note: \* Temperature and relative humidity of air during the test: +20°C, 60%; TM – test method of FEICA association; PN – company standard; DIN – German standard;

#### **Packaging**

The product is supplied in a pressure cans with a filling volume from 870 ml to 300 ml. Packing in cartons of 12 pcs. Palette contains 624/672/780/840/960/1176 cans.

#### Storage

Store the cans in the vertical position with the valve facing upwards. Keep in a dry and well-ventilated place at a temperature between +5°C to 25°C. Guaranteed shelf life of the product is 18 months from the date of production.

Date of issue: 16.08.2005
Datum 5<sup>th</sup> revision: 01.03.2020