

Technical data sheet

PU ROOF TILES ADHESIVE GUN GRADE B3

51

Description

Polyurethane adhesive for roof tiles is an excellent adhesive with extremely low additional expansion. It is specially developed for installing roof tiles and/or repairing roof cladding.

Application

The PU adhesive for roof tiles can be used for bonding of all types of roof tiles (clay and concrete) and also some other building and/or roofing materials (metal, wooden shingle, bitumen, wood).

Application procedure

- 1 Remove dust, grease and other contamination from the surface. Before the foam application the surface may be wet, but free from frost or ice.
NOTICE: PU foam is non-stick to surfaces: PE, PP, PTFE and silicone.
- 2 The optimal can temperature for application is +15°C to +20°C. The maximum allowed temperature difference between the ambient and the can is 5°C. Do not exceed the maximum allowed temperature interval for application from +5°C to +35°C.
- 3 Shake the can vigorously at least for 1 minute. Screw the can onto the application gun. Bottle working position is the valve facing downwards. The amount of ejected foam can be regulated by pulling the gun trigger.
Apply a sufficient amount of foam on the glued element and to press it to the substrate. Minor corrections of element position are possible within 10 minutes after application.
- 4 Cured foam you can cut by a knife. The surface of cured PU foam must be protected from a long-term UV radiation.
- 5 Fresh foam can be removed by PU CLEANER, cured foam mechanically only. The gun must be cleaned by PU cleaner immediately after finishing work i.e. after removing the bottles from the gun. Before screwing the cleaner onto the gun connector, put a plastic tube, which is included in the gun package. This prevents aerosol formation during cleaning.

Safety and protection of health

When using this product wear protective glasses and gloves. More information is contained in the MSDS.

Specifications

Form	foaming liquid
Colour	light cream, blue, green, grey
Odour	of hydrocarbons
Maximum application temperatures range	+5°C to +35°C
Optimum can temperature for application	+15°C to +20°C
Tack free time (TM1014-2013) *	10 minutes
Cutting time (strip of 2 cm diameter) (TM1005-2013) *	max. 25 minutes
Final curing time *	12 hours
Density of freely expanded foam (PN 03) *	14 – 18 kg/m ³
Density of foam in gap (PN05) *	18 – 22 kg/m ³
Foam yield of 750 ml can (TM1007-2013) *	40 – 45 litres
Dimensional stability (TM1004-2013) *	max. ±5%
Fire class (DIN 4102)	B3

Note: * Temperature and relative humidity of air during the test: +20°C, 60%; TM – test method of FEICA association; PN – company standard; DIN – German standard;

Packaging

The product is supplied in a pressure cans with a filling volume from 870 ml to 500 ml. Packing in cartons of 12 pcs. Palette contains 624/672/780/840/960/1008 cans.

Storage

Store the cans in the vertical position with the valve facing upwards. Keep in a dry and well-ventilated place at a temperature between +5°C to +25°C. Guaranteed shelf life of the product is 18 months from the date of production.

Date of issue: 10.01.2012
Datum 5th revision: 01.09.2020