

AEROSOL – SERVICE a.s. Družstevní 2, 273 51 Pletený Újezd, Czech Republic

Technical Data Sheet No.: 12

Date of issue: 11.01.2017

Date of 3rd revision: 11.01.2017

PU FOAM WATER-WELL HAND HELD B3

Description

Water-Well Polyurethane Foam is installation and insulation polyurethane foam expanded by foaming and hardening of the fluid reaction mixture by the effect of aerial moisture. The foam is specially formulated to be used mainly for applications involving direct contact with potable water.

Application

The main applications of water well PU foam include sealing and gluing of water well rings, sewage piping or waste water gutters, sealing of inspection shaft etc.

Application procedure

- Remove dust, grease and other contamination from the surface. Before the foam application the surface may be wet, but free from frost or ice cover.
 - **NOTICE**: PU foam is non-stick to surfaces: PE, PP, PTFE and silicone.
- 2 The optimal can temperature for application is +15 °C to +20°C. The maximum allowed temperature difference between the ambient and the can is 5 °C. Do not exceed the maximum allowed temperature interval for application from +5 °C to +35 °C.
- 3 Moisten surfaces with water applied from a spray bottle. Shake the can vigorously at least for 1 minute. Screw the plastic applicator on the valve. Bottle working position is the valve facing downwards. The amount of ejected foam can be regulated by pulling the applicator handle. If the cavity is wider than 5 cm we recommend to fill it in layers with maximal width of 2 cm. Wet the surface of each fresh foam layer and continue by adding other layer(s) until the space is filled up. The foam will expand during curing; therefore fill the space only up to 1/2. Volume and quality of cured foam is influenced by the relative air humidity. Intensive moistening is necessary if relative air humidity is below 35 %.
- 4 Cured foam you can cut by a knife. The surface of cured PU foam must be protected from a long-term UV radiation.
- Fresh foam can be removed by PU CLEANER, cured foam mechanically only. When the work is interrupted for more than 10 - 15 min, there is necessary to clean up application tube and by PU CLEANER.

Packaging

The product is supplied in a pressure cans with a filling volume from 870 ml to 300 ml. Packing in cartons of 12 pcs.

Palette contains 624/672/780/840/960/1008/1176 cans.

Specifications

Form	foaming liquid
Colour	light cream, blue, green, grey
Odour	of hydrocarbons
Maximum application temperatures range	+5°C to +35°C
Optimum can temperature for application	+15°C to +20°C
Minimum contact surface temperature	0°C
Tack free time (TM1014-2013) *	12 minutes
Cutting time (strip of 2 cm diameter) (TM1005-2013) *	max. 40 minutes
Final curing time *	12 hours
Density of freely expanded foam (PN 03) *	18 - 22 kg/m ³
Density of foam in gap (PN05) *	22 - 25 kg/m ³
Foam yield of 750 ml container (TM1007-2013) *	28 - 32 litres
Dimensional stability (TM1004-2013) *	max. ±5%
Fire class (DIN 4102) / (EN 13501-1)	B3 / F
Certification for contact with drinking water (according to Decree of Czech Ministery of Health, A. 409/2005 Coll.)	YES

Note: TM – test method of FEICA association; PN – company standard DIN – German standard; EN – European standard

Polyurethane foam meets the requirements for contact with potable wate - for details see Protocol No. 32100/2011 dated 27.12.2011 issued by Institute of Public Health in Pilsen, Czech Republic (Accredited testing laboratory No. 1384)

Storage

Store the cans in the vertical position with the valve facing upwards. Keep in a dry and well ventilated place at a temperature between +5°C to 25°C. Guaranteed shelf life of the product is 18 months from the date of production.

Safety and protection of health

When using this product wear protective glasses and gloves. More information is contained in the MSDS.

tel.: +420 312 690 505 fax: +420 312 690 503 e-mail: aerosol@aerosol.cz

IČO: 241 23 145 DIČ: CZ 241 23 145

^{*} Temperature and relative humidity of air during the test: +20°C, 60%